

# MUTUAL CORNELL

Irene and Danel  
Giometal Co., Ltd  
No. 4, Zhenlong Road, 5th Industrial Park Caiwu  
Wusha, Chang'an Town, Dongguan City, GuangDong, China, 523850

December 2, 2021

CERTIFICATE OF ANALYSIS  
Date Submitted: 11/30/2021

## XRF Assay Composition

Sample Desc.: 14k 2.5mm Bezel CZ  
Sample Date: 11/25/2021

Date Analyzed: 12/02/2021  
Analyzed by: MS

Revised

	Results	Unit
<b>Gold Tone Section</b>		
Copper	30.852	%/wt.
Gold	58.530	%/wt.
Nickel	0.208	%/wt.
Silver	4.534	%/wt.
Zinc	5.876	%/wt.



**Revision Note: Fixed the error with the results not feeding from the correct location. MS**



Kevin E. Donahue  
Laboratory Director



Jeff Mascoli  
Laboratory Manager

The above results were obtained using a Fischer Technologies Fischerscope XAN-DPP-X-Ray Fluoroscope (XRF).  
After grinding test results indicate the approximate assay composition of the substrate base metal only.  
The measurement error is within +/- 5.0% of the measured values per typical instrumental methods.  
Samples submitted by customer, results relate only to items tested.  
Test report shall not be reproduced except in full, without written approval of the laboratory.

Pg. 1 of 1