

MUTUAL CORNELL

Irene and Danel
Giometal Co., Ltd

No. 4, Zhenlong Road, 5th Industrial Park Caiwu
Wusha, Chang'an Town, Dongguan City, GuangDong, China, 523850

CERTIFICATE OF ANALYSIS
Date Submitted: 11/30/2021

December 2, 2021

XRF Assay Composition

Sample Desc.: Small Ball 14K 4mm
Sample Date: 11/25/2021


Date Analyzed: 12/02/2021
Analyzed by: MS

	Results	Unit
Gold Tone Section		
Copper	30.676	%/wt.
Gold	58.362	%/wt.
Nickel	0.364	%/wt.
Silver	4.428	%/wt.
Zinc	6.170	%/wt.





Kevin E. Donahue
Laboratory Director



Jeff Mascoli
Laboratory Manager

The above results were obtained using a Fischer Technologies Fischerscope XAN-DPP-X-Ray Fluoroscope (XRF).
After grinding test results indicate the approximate assay composition of the substrate base metal only.
The measurement error is within +/- 5.0% of the measured values per typical instrumental methods.
Samples submitted by customer, results relate only to items tested.
Test report shall not be reproduced except in full, without written approval of the laboratory.

Pg. 1 of 1